



**RESISTANCE TO SOLVENTS OF MARKING,
MATERIALS AND FINISHES**

ESCC Basic Specification No. 24800

Issue 3	February 2014
---------	---------------



LEGAL DISCLAIMER AND COPYRIGHT

European Space Agency, Copyright © 2014. All rights reserved.

The European Space Agency disclaims any liability or responsibility, to any person or entity, with respect to any loss or damage caused, or alleged to be caused, directly or indirectly by the use and application of this ESCC publication.

This publication, without the prior permission of the European Space Agency and provided that it is not used for a commercial purpose, may be:

- copied in whole, in any medium, without alteration or modification.
- copied in part, in any medium, provided that the ESCC document identification, comprising the ESCC symbol, document number and document issue, is removed.

DOCUMENTATION CHANGE NOTICE

(Refer to <https://escies.org> for ESCC DCR content)

DCR No.	CHANGE DESCRIPTION
838	Specification upissued to incorporate editorial changes per DCR.

**TABLE OF CONTENTS**

1	SCOPE	5
1.1	GENERAL	5
1.2	PURPOSE	5
2	TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS	5
3	REQUIREMENTS	5
3.1	GENERAL	5
3.1.1	Formulation of Solvents	5
3.1.2	Check for Conflicts	5
3.1.3	Applicability	5
3.2	MATERIALS	5
3.2.1	Solvent Solutions	5
3.2.2	Vessel	6
3.2.3	Brush	6
4	PROCEDURES	6

1 SCOPE

1.1 GENERAL

This specification defines the basic requirements applicable to the resistance to solvents of marking, materials and finishes for electrical, electronic and electro-mechanical components suitable for space application.

1.2 PURPOSE

The purpose of this test is to verify that the markings or colour-coding will not become illegible or discoloured on the component parts (including printed-wiring boards) when subjected to solvents (normally used to clean solder-flux, fingerprints and other contaminants from printed-wiring and terminal board assemblies, etc.). The solvents will not cause deleterious effects, or mechanical or electrical damage, or deterioration of the materials or finishes.

2 TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS

The terms, definitions, abbreviations, symbols and units specified in ESCC Basic Specification No. 21300 shall apply.

3 REQUIREMENTS

3.1 GENERAL

3.1.1 Formulation of Solvents

The formulation of solvents herein is considered typical and representative of the desired stringency as far as the usual coatings and markings are concerned.

3.1.2 Check for Conflicts

When this test is referenced, care shall be exercised to assure that conflicting requirements, as far as the properties of the specified finishes and markings are concerned, are not invoked.

3.1.3 Applicability

Unless otherwise specified, this test shall be considered not applicable to components that have no actual markings or colour-coding on the components, or are marked exclusively using a permanent engraving or etching process.

3.2 MATERIALS

3.2.1 Solvent Solutions

The solvent solutions used in this test shall consist of the following:

- (a) Ethyl alcohol, 99.5% or 95% pure by volume.
- (b) Isopropyl alcohol, 99% pure.
- (c) De-ionised water at +40°C maximum may be used for certain fluxes. Items shall be thoroughly dried directly after the use of de-ionised water.

3.2.2 Vessel

The vessel shall be a container made of inert material and of sufficient size to permit complete immersion of the specimens in the solvent solutions specified in Para. 3.2.1.

3.2.3 Brush

The brush shall be a toothbrush with a handle made of a non-reactive material. The brush shall have three long rows of hard bristles, the free ends of which shall lie substantially in the same horizontal plane. The toothbrush shall be discarded at the completion of each test.

4 **PROCEDURES**

Unless otherwise specified in the relevant Generic Specification the specimens subjected to this test shall be divided into two groups with a minimum quantity of one component per group. Each group shall be individually subjected to one of the following procedures:

- (a) The first group shall be subjected to the solvent solution specified in Para. 3.2.1(a).
- (b) The second group shall be subjected to the solvent solution specified in Para. 3.2.1(b).

The solution shall be maintained at a temperature of $+25 \pm 5$ °C.

The specimens shall be completely immersed for one minute in the specified solution contained in the vessel specified in Para. 3.2.2. Immediately following immersion, each specimen shall be brushed with normal hand pressure for ten strokes over all that area of the component which contains marking, with the brush specified in Para. 3.2.3. Immediately after brushing, the above procedure shall be repeated two additional times, for a total of three immersions followed by brushings. The brush stroke shall be directed in a forward direction, across the surface of the specimen being tested. After five minutes, the specimens shall be examined to determine the extent of any deterioration that has occurred.

Where a transparent, insulating sleeve covers the component body and protects the marking, the component Manufacturer may elect to conduct the permanence of marking test on the component body with the sleeve removed, and to separately test the sleeve material for resistance to deterioration caused by the solvent solutions.

In all cases where the component Manufacturer elects to test the marking with the sleeve removed, the complete test procedure and sequence, including the tests on the sleeve material, shall be fully defined in the Process Identification Document (PID).