

Page 1 of 17

# CAPACITORS, MICROWAVE, SILICON, MOS, NAKED DIE

**BASED ON TYPES 101M, 201M, 400M AND 401M** 

ESCC Detail Specification No. 5711/002

Issue 3 May 2015



Document Custodian: European Space Agency - see <a href="https://escies.org">https://escies.org</a>



#### **LEGAL DISCLAIMER AND COPYRIGHT**

European Space Agency, Copyright © 2015. All rights reserved.

The European Space Agency disclaims any liability or responsibility, to any person or entity, with respect to any loss or damage caused, or alleged to be caused, directly or indirectly by the use and application of this ESCC publication.

This publication, without the prior permission of the European Space Agency and provided that it is not used for a commercial purpose, may be:

- copied in whole, in any medium, without alteration or modification.
- copied in part, in any medium, provided that the ESCC document identification, comprising the ESCC symbol, document number and document issue, is removed.

**ISSUE 3** 

### **DOCUMENTATION CHANGE NOTICE**

(Refer to <a href="https://escies.org">https://escies.org</a> for ESCC DCR content)

DCR No.	CHANGE DESCRIPTION
919	Specification upissued to incorporate changes per DCR.



### ESCC Detail Specification

No. 5711/002 ISSUE 3

PAGE 4

### **TABLE OF CONTENTS**

1	GENERAL	5
1.1	SCOPE	5
1.2	APPLICABLE DOCUMENTS	5
1.3	TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS	5
1.4	THE ESCC COMPONENT NUMBER AND COMPONENT TYPE VARIANTS	5
1.4.1	The ESCC Component Number	5
1.4.1.1	Characteristics and Ratings Codes	5
1.4.2	Component Type Variants and Range of Components	6
1.5	MAXIMUM RATINGS	7
1.6	HANDLING PRECAUTIONS	8
1.7	PHYSICAL DIMENSIONS	8
1.7.1	Variants 01 to 10	8
1.7.2	Variants 11 to 23	8
1.7.3	Variants 24, 25, 26	9
1.7.4	Variants 27, 28 and 29	10
1.7.5	Variant 30	11
1.7.6	Variant 31	12
1.8	FUNCTIONAL DIAGRAM	12
1.9	MATERIALS AND FINISHES	12
2	REQUIREMENTS	13
2.1	GENERAL	13
2.1.1	Deviations from the Generic Specification	13
2.1.1.1	Deviations from Production Control (Chart F2)	13
2.1.1.2	Deviations from Screening Tests (Chart F3)	13
2.2	MARKING	13
2.3	DIE SHEAR	13
2.4	ELECTRICAL MEASUREMENTS AT ROOM, HIGH AND LOW TEMPERATURES	14
2.4.1	Room Temperature Electrical Measurements	14
2.4.2	High and Low Temperatures Electrical Measurements	14
2.5	PARAMETER DRIFT VALUES	15
2.6	INTERMEDIATE AND END-POINT ELECTRICAL MEASUREMENTS	15
2.7	BURN-IN 2 CONDITIONS	16
2.8	OPERATING LIFE CONDITIONS	16
APPEND	IX A	17



#### 1 GENERAL

#### 1.1 SCOPE

This specification details the ratings, physical and electrical characteristics and test and inspection data for the component type variants and/or the range of components specified below. It supplements the requirements of, and shall be read in conjunction with, the ESCC Generic Specification listed under Applicable Documents.

#### 1.2 APPLICABLE DOCUMENTS

The following documents form part of this specification and shall be read in conjunction with it:

- (a) ESCC Generic Specification No. 5010
- (b) MIL-STD-750, Test Methods and Procedures for Semiconductor Devices

#### 1.3 TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS

For the purpose of this specification, the terms, definitions, abbreviations, symbols and units specified in ESCC Basic Specification No. 21300 shall apply.

#### 1.4 THE ESCC COMPONENT NUMBER AND COMPONENT TYPE VARIANTS

#### 1.4.1 The ESCC Component Number

The ESCC Component Number shall be constituted as follows:

Example: 5711002012C2KG

- Detail Specification Reference: 5711002
- Component Type Variant Number: 01 (as required)
- Characteristic code: Capacitance Value (2.2pF): 2C2 (as required)
- Characteristic code: Tolerance (±10%): K (as required)
- Rating code: Rated Voltage (200V): G (as required)

#### 1.4.1.1 Characteristics and Ratings Codes

Characteristics and ratings to be codified as part of the ESCC Component Number shall be as follows:

(a) Rated Capacitance Value  $C_n$  expressed by means of the following codes in accordance with ESCC Basic Specification No. 21700. The unit quantity shall be picofarads (pF):

Capacitance Value C <sub>n</sub> (pF)	Code
0.XX	CXX
X.X	XCX
XX	XX0
XX10 <sup>1</sup>	XX1



(b) Capacitance Tolerance expressed by the following codes in accordance with ESCC Basic Specification No. 21700:

Tolerance (± %)	Code Letter
10	K
20	M

(c) Rated Voltage expressed by the following codes:

Rated Voltage U <sub>R</sub> (V)	Code Letter
40	В
100	E
200	G
400	К

#### 1.4.2 <u>Component Type Variants and Range of Components</u>

The component type variants and the associated range of components applicable to this specification are as follows:

Variant Number	Based on Type	Capacitance Values C <sub>n</sub> (pF)	Capacitance Tolerance (± %)	Rated Voltage U <sub>R</sub> (V)
01	201M106C	2.2, 2.7, 3.3	10, 20	200
02	101M106C	3.9, 4.7, 5.6, 6.8	10, 20	100
03	400M106C	8.2, 10, 12, 15	10, 20	40
04	201M107C	3.9, 4.7, 5.6, 6.8, 8.2	10, 20	200
05	101M107C	10, 12, 15	10, 20	100
06	400M107C	18, 22, 27, 33, 39	10, 20	40
07	201M108C	10, 12, 15, 18	10, 20	200
08	101M108C	22, 27, 33, 39	10, 20	100
09	400M108C	47, 56, 68	10, 20	40
10	400M110C	82, 100	10, 20	40
11	201M106A	0.22, 0.27, 0.33, 0.39, 0.47, 0.56, 0.68, 0.82, 1, 1.2, 1.5, 1.8, 2.2, 2.7, 3.3	10, 20	200
12	101M106A	3.9, 4.7, 5.6, 6.8	10, 20	100
13	400M106A	8.2, 10, 12, 15	10, 20	40
14	201M104A	3.9, 4.7, 5.6, 6.8	10, 20	200
15	101M104A	10, 12	10, 20	100
16	400M104A	18, 22, 27	10, 20	40
17	201M107A	8.2	10, 20	200
18	101M107A	15	10, 20	100



Variant Number	Based on Type	Capacitance Values C <sub>n</sub> (pF)	Capacitance Tolerance (± %)	Rated Voltage U <sub>R</sub> (V)
19	400M107A	33, 39	10, 20	40
20	201M108A	10, 12, 15, 18	10, 20	200
21	101M108A	22, 27, 33, 39	10, 20	100
22	400M108A	47, 56, 68	10, 20	40
23	400M110A	82, 100	10, 20	40
24	401M111J	0.125 (Note 1)	10, 20	400
25	201M111J	0.25 (Note 1)	10, 20	200
26	101M111J	0.5 (Note 1)	10, 20	100
27	401M112J	0.2 (Note 1)	10, 20	400
28	201M112J	0.4 (Note 1)	10, 20	200
29	101M112J	0.8 (Note 1)	10, 20	100
30	400M113J	10 (Note 1)	10, 20	40
31	400M114J	10 (Note 1)	10, 20	40

#### **NOTES:**

1. Capacitor arrays with several bond pads. The capacitance value refers to C<sub>n</sub>, the smallest individual rated capacitance value available on the die. Multiples of C<sub>n</sub> also available on the die shall be as specified in Physical Dimensions for the particular Variant.

#### 1.5 <u>MAXIMUM RATINGS</u>

The maximum ratings shall not be exceeded at any time during use or storage.

Maximum ratings shall only be exceeded during testing to the extent specified in this specification and when stipulated in Test Methods and Procedures of the ESCC Generic Specification.

Characteristics	Symbols	Maximum Ratings	Unit	Remarks
Rated Voltage	$U_R$	See Component Type Variants and Range of Components	V	
Breakdown Voltage	$V_{BR}$	1.5U <sub>R</sub>	V	Minimum
Operating Temperature Range	$T_{op}$	-55 to +150	°C	$T_{amb}$
Storage Temperature Range	$T_{stg}$	-55 to +175	°C	
Die Attach Temperature	T <sub>die</sub>	+320	ç	Note 1

#### NOTES:

1. Duration 30 seconds maximum.




#### 1.6 <u>HANDLING PRECAUTIONS</u>

These devices are susceptible to damage by electrostatic discharge. Therefore suitable precautions shall be employed for protection during all phases of manufacture, test, packaging, shipping and handling.

These components are categorised as Class 1 per ESCC Basic Specification No. 23800 with a minimum Critical Path Failure Voltage of 1000V.


#### 1.7 PHYSICAL DIMENSIONS

#### 1.7.1 <u>Variants 01 to 10</u>




Symbols	Dimensions mm		Variant Number
	Min	Max	Number
А	0.34	0.4	01, 02, 03
	0.54	0.6	04, 05, 06
	0.74	0.8	07, 08, 09
	0.94	1	10
ØC	0.145	0.31	01, 02, 03
	0.31	0.49	04, 05, 06
	0.54	0.66	07, 08, 09
	0.72	0.78	10
Е	0.16	0.22	All

#### 1.7.2 <u>Variants 11 to 23</u>



Symbols	Dimensions mm		Variant Number
	Min	Max	Number
Α	0.3	0.4	11, 12, 13
	0.44	0.54	14, 15, 16
	0.5	0.6	17, 18, 19
	0.7	0.8	20, 21, 22
	0.9	1	23
D	0.22	0.28	11, 12, 13
	0.34	0.38	14, 15, 16
	0.4	0.44	17, 18, 19
	0.54	0.64	20, 21, 22
	0.68	0.78	23
E	0.16	0.22	All

#### 1.7.3 Variants 24, 25, 26




NOTES:

1. Dimension of the smallest bond pad area, specified for bonding purposes.




#### 1.7.4 Variants 27, 28 and 29



NOTES: 1. Dim Dimension of the smallest bond pad area, specified for bonding purposes.

#### 1.7.5 Variant 30




Symbols	Dimensions mm		Notes
	Min Max		
А	0.4	0.5	
D	0.06	0.08	1
Е	0.16	0.22	
F	0.26	0.28	1

NOTES:

1. Dimension of the smallest bond pad area, specified for bonding purposes.

### 1.7.6 <u>Variant 31</u>




Symbols	Dimensions mm		Notes
	Min Max		
А	0.4	0.5	
D	0.06	0.08	1
Е	0.16	0.22	
F	0.26	0.28	1

#### **NOTES:**

1. Dimension of the smallest bond pad area, specified for bonding purposes.

#### 1.8 <u>FUNCTIONAL DIAGRAM</u>



#### 1.9 MATERIALS AND FINISHES

Materials and finishes shall be as follows:

- (a) Bond Pad
  - The bond pad metallisation shall be TiAu with a layer of vacuum-deposited gold, thickness  $\geq 0.25\mu m$  and a final layer of electrolytic gold, thickness  $\geq 2.7\mu m$ .
- (b) Die Backface

  The die backface metallisation shall be TiAu with a layer of gold, thickness ≥ 0.5μm.



#### 2 REQUIREMENTS

#### 2.1 GENERAL

The complete requirements for procurement of the components specified herein are as stated in this specification and the ESCC Generic Specification. Permitted deviations from the Generic Specification, applicable to this specification only, are listed below.

Permitted deviations from the Generic Specification and this Detail Specification, formally agreed with specific Manufacturers on the basis that the alternative requirements are equivalent to the ESCC requirement and do not affect the component's reliability, are listed in the appendices attached to this specification.

#### 2.1.1 Deviations from the Generic Specification

#### 2.1.1.1 Deviations from Production Control (Chart F2)

(a) A Metallisation Adhesion test shall be performed on a randomly selected sample of 5 naked die from each wafer lot, after Die Visual Inspection during Wafer Lot Acceptance. Samples shall be subjected to a high temperature bake of +320 (+5 -0)°C for a period of 5 minutes minimum. The samples shall then be visually inspected. Any evidence of lifting or peeling metallisation shall be cause for wafer lot failure. This test is considered as destructive and therefore components so tested shall not form part of the delivery lot.

#### 2.1.1.2 Deviations from Screening Tests (Chart F3)

- (a) Burn-in 1: Not applicable.
- (b) Parameter Drift Values Δ1: Not applicable.
- (c) Check for Lot Failure for Burn-in 1: Not applicable.

#### 2.2 MARKING

The marking shall be in accordance with the requirements of ESCC Basic Specification No. 21700.

The information to be marked and the order of precedence shall be as follows:

- (a) The ESCC qualified components symbol (for ESCC qualified components only).
- (b) The ESCC Component Number.
- (c) Traceability information.

#### 2.3 DIE SHEAR

In those cases where package clearances are such that a die shear test is not practicable, the die shall be pushed away with a suitable tool. The force required to remove the die need not be recorded. The die attachment area shall be inspected and the component shall be considered acceptable if more than 50% of the semiconductor material remains.



#### 2.4 <u>ELECTRICAL MEASUREMENTS AT ROOM, HIGH AND LOW TEMPERATURES</u>

#### 2.4.1 Room Temperature Electrical Measurements

The measurements shall be performed at  $T_{amb}$  = +22 ±3°C.

Characteristics	Symbols	MIL-STD-750 Test Method	Test Conditions	Tolerance (± %)	Lin	nits	Units
				(= /0)	Min	Max	
Capacitance	С	4001	V <sub>T</sub> = 0V, f = 1MHz	10 20	0.9C <sub>n</sub> 0.8C <sub>n</sub>	1.1C <sub>n</sub> 1.2C <sub>n</sub>	pF
Leakage Current	I <sub>L1</sub>	4016	$V_T = U_R$	All	-	50	nA
Voltage Proof Leakage Current	I <sub>L2</sub>	4016	$V_T = 1.5U_R$	All	-	100	nA

### 2.4.2 <u>High and Low Temperatures Electrical Measurements</u>

Characteristics	Symbols	MIL-STD-750 Test Method	Test Conditions Note 1	Lim	Limits	
				Min	Max	
Leakage Current	I <sub>L1</sub>	4016	$T_{amb} = +150 (+0 -3)^{\circ}C$ $V_{T} = U_{R}$	-	100	nA

#### **NOTES:**

1. Measurements shall be performed on a sample basis as specified in the Generic Specification.



#### 2.5 PARAMETER DRIFT VALUES

Unless otherwise specified, the measurements shall be performed at  $T_{amb}$  = +22 ±3°C.

The test methods and test conditions shall be as per the corresponding test defined in Room Temperature Electrical Measurements.

The drift values ( $\Delta$ ) shall not be exceeded for each characteristic specified. The corresponding absolute limit values for each characteristic shall not be exceeded.

Characteristics	Symbols		Limits		Units
		Drift Value	Absolute		
		Δ	Min	Max	
Capacitance	С	±0.2 or (1) ±2%	Note 2		pF
Leakage Current	I <sub>L1</sub>	±5 or (1) ±100%	-	50	nA

#### NOTES:

- 1. Whichever is the greater referred to the initial value.
- 2. As specified in Room Temperature Electrical Measurements.

#### 2.6 <u>INTERMEDIATE AND END-POINT ELECTRICAL MEASUREMENTS</u>

Unless otherwise specified, the measurements shall be performed at  $T_{amb} = +22 \pm 3^{\circ}C$ .

The test methods and test conditions shall be as per the corresponding test defined in Room Temperature Electrical Measurements.

The limit values for each characteristic shall not be exceeded.

Characteristics	Symbols	Limits		Units
		Min	Max	
Capacitance	С	Note 1		pF
Leakage Current	I <sub>L1</sub>	-	50	nA
Voltage Proof Leakage Current	I <sub>L2</sub>	-	100	nA

#### NOTES:

1. As specified in Room Temperature Electrical Measurements.



### 2.7 BURN-IN 2 CONDITIONS

Characteristics	Symbols	Test Conditions	Units
Ambient Temperature	T <sub>amb</sub>	+150 (+0 -3)	°C
Test Voltage	V <sub>T</sub>	U <sub>R</sub>	V

### 2.8 OPERATING LIFE CONDITIONS

The conditions shall be as specified for Burn-in 2.



## APPENDIX A AGREED DEVIATIONS FOR COBHAM MICROWAVE (F)

Items Affected	Description of Deviations		
Deviations from Generic Specification: Special In-Process Controls (Chart F2)	Assembly (Assembly of the Packaged Test Sublot for Naked Die Components): A minimum of 5 dice per wafer and 20 dice per wafer lot shall be assembled to make up the Packaged Test Sublot.		
	Encapsulation: Encapsulation of the Packaged Test Sublot samples is optional at the Manufacturer's discretion.		
Deviations from Generic	Particle Impact Noise Detection (PIND): Not applicable.		
Specification: Screening Tests (Chart F3)	Radiographic Inspection: Not applicable.		
	Seal (Fine and Gross Leak): Not applicable.		
	External Visual Inspection: Not applicable.		