

Page 1 of 12

## CAPACITORS, FIXED, CHIPS, CERAMIC DIELECTRIC, TYPE I

## BASED ON TYPE 0603

ESCC Detail Specification No. 3009/037



Document Custodian: European Space Agency – see https://escies.org



PAGE 2

**ISSUE 4** 

#### LEGAL DISCLAIMER AND COPYRIGHT

European Space Agency, Copyright © 2021. All rights reserved.

The European Space Agency disclaims any liability or responsibility, to any person or entity, with respect to any loss or damage caused, or alleged to be caused, directly or indirectly by the use and application of this ESCC publication.

This publication, without the prior permission of the European Space Agency and provided that it is not used for a commercial purpose, may be:

- copied in whole, in any medium, without alteration or modification.
- copied in part, in any medium, provided that the ESCC document identification, comprising the ESCC symbol, document number and document issue, is removed.



PAGE 3

**ISSUE 4** 

### **DOCUMENTATION CHANGE NOTICE**

(Refer to https://escies.org for ESCC DCR content)

| DCR No. | CHANGE DESCRIPTION                                    |
|---------|---|
| 1460    | Specification updated to incorporate changes per DCR. |



**ISSUE 4** 

## TABLE OF CONTENTS

| 1     | GENERAL  | 5  |
|-------|--|----|
| 1.1   | SCOPE  | 5  |
| 1.2   | APPLICABLE DOCUMENTS                                       | 5  |
| 1.3   | TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS       | 5  |
| 1.4   | THE ESCC COMPONENT NUMBER AND COMPONENT TYPE VARIANTS      | 5  |
| 1.4.1 | The ESCC Component Number                                  | 5  |
| 1.4.2 | Component Type Variants and Range of Components            | 6  |
| 1.5   | MAXIMUM RATINGS  | 8  |
| 1.6   | PHYSICAL DIMENSIONS  | 8  |
| 1.7   | FUNCTIONAL DIAGRAM   | 8  |
| 2     | REQUIREMENTS   | 9  |
| 2.1   | GENERAL  | 9  |
| 2.1.1 | Deviations from the Generic Specification                  | 9  |
| 2.2   | MARKING  | 9  |
| 2.3   | ELECTRICAL MEASUREMENTS AT ROOM, HIGH AND LOW TEMPERATURES | 10 |
| 2.3.1 | Room Temperature Electrical Measurements                   | 10 |
| 2.3.2 | High and Low Temperatures Electrical Measurements          | 10 |
| 2.4   | INTERMEDIATE AND END-POINT ELECTRICAL MEASUREMENTS         | 11 |
| 2.5   | BURN-IN  | 12 |



PAGE 5

ISSUE 4

#### 1 <u>GENERAL</u>

#### 1.1 <u>SCOPE</u>

This specification details the ratings, physical and electrical characteristics, and test and inspection data for the component type variants and/or the range of components specified below. It supplements the requirements of, and shall be read in conjunction with, the ESCC Generic Specification listed under Applicable Documents.

#### 1.2 <u>APPLICABLE DOCUMENTS</u>

The following documents form part of this specification and shall be read in conjunction with it:

(a) ESCC Generic Specification No. 3009.

## 1.3 TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS

For the purpose of this specification, the terms, definitions, abbreviations, symbols and units specified in ESCC Basic Specification No. 21300 shall apply.

#### 1.4 THE ESCC COMPONENT NUMBER AND COMPONENT TYPE VARIANTS

# 1.4.1 The ESCC Component Number The ESCC Component Number shall be constituted as follows:

Example: 3009037011000KC

- Detail Specification Reference: 3009037
- Component Type Variant Number: 01 (as required)
- Characteristic code: Capacitance Value (100pF): 1000 (as required)
- Characteristic code: Capacitance Tolerance (±5%): K (as required)
- Rating code: Rated Voltage (50V): C (as required)

#### 1.4.1.1 Characteristics and Ratings Codes

Characteristics and ratings to be codified as part of the ESCC Component Number shall be as follows:

(a) Rated Capacitance Value, C<sub>n</sub>, expressed by means of the following codes in accordance with ESCC Basic Specification No. 21700. The unit quantity shall be picofarad (pF).

| Capacitance Value C <sub>n</sub><br>(pF) | Code |
|--|------|
| X.XX                                     | XCXX |
| XX.X                                     | XXCX |
| XXX                                      | XXX0 |
| XXX 10 <sup>1</sup>                      | XXX1 |

ESCC Detail Specification

No. 3009/037



ISSUE 4

(b) Capacitance Tolerance expressed by the following codes in accordance with ESCC Basic Specification No. 21700:

| Tolerance<br>(±) | Code Letter | Remark                    |
|------------------|-------------|---------------------------|
| 0.25pF           | С           |                           |
| 0.5pF            | D           |                           |
| 1pF              | F           | For C <sub>n</sub> < 10pF |
| 1%               | F           | For C <sub>n</sub> ≥ 10pF |
| 2%               | G           |                           |
| 5%               | J           |                           |
| 10%              | К           |                           |

(c) Rated Voltage,  $U_{R}$ , expressed by the following codes:

| Rated Voltage U <sub>R</sub><br>(V) | Code Letter |
|-------------------------------------|-------------|
| 16                                  | Х           |
| 25                                  | A           |
| 50                                  | С           |
| 100                                 | E           |
| 200                                 | G           |

## 1.4.2 Component Type Variants and Range of Components

The component type variants and range of components applicable to this specification are as follows:

| Variant | Style | Capacitance                           | Terminal Mate    | erial and Finish                 | Weight<br>Max |
|---------|-------|---------------------------------------|------------------|----------------------------------|---------------|
| Number  |       | Range,<br>Tolerance,<br>Rated Voltage | End Terminations | Termination Finish               | (g)           |
| 01      | 0603  | See Note 1                            | Ag/Pd            | No finish (Note 2)               | 0.1           |
| 03      | 0603  | See Note 1                            | Ag/Pd/Pt         | No finish (Note 2)               | 0.1           |
| 05      | 0603  | See Note 1                            | Ag + Ni barrier  | Sn60, Sn62 or<br>Sn63 solder dip | 0.1           |
| 06      | 0603  | See Note 1                            | Ag + Ni barrier  | Sn/Pb plating<br>(Note 3)        | 0.1           |
| 08      | 0603  | See Note 1                            | Ag + Ni barrier  | Au plating (Note 2)              | 0.1           |



ISSUE 4

## NOTES:

1. Available rated voltages, capacitance values and tolerances are as follows:

| Rated<br>Voltage U <sub>R</sub> |     | ce Range C <sub>n</sub><br>pF) | Tolerance<br>(±) | Value<br>Series |
|---------------------------------|-----|--------------------------------|------------------|-----------------|
| (V)                             | Min | Max                            |                  |                 |
| 200                             | 1   | 9.53                           | 0.25pF           | E48             |
|                                 |     | 9.1                            | 0.5pF            | E24             |
|                                 |     | 8.2                            | 1pF              | E12             |
|                                 | 10  | 100                            | 1%               | E96             |
|                                 |     |                                | 2%               | E48             |
|                                 |     |                                | 5%               | E24             |
|                                 |     |                                | 10%              | E12             |
| 100                             | 1   | 9.53                           | 0.25pF           | E48             |
|                                 |     | 9.1                            | 0.5pF            | E24             |
|                                 |     | 8.2                            | 1pF              | E12             |
|                                 | 10  | 332                            | 1%               | E96             |
|                                 |     |                                | 2%               | E48             |
|                                 |     | 330                            | 5%               | E24             |
|                                 |     |                                | 10%              | E12             |
| 50                              | 1   | 9.53                           | 0.25pF           | E48             |
|                                 |     | 9.1                            | 0.5pF            | E24             |
|                                 |     | 8.2                            | 1pF              | E12             |
|                                 | 10  | 562                            | 1%               | E96             |
|                                 |     |                                | 2%               | E48             |
|                                 |     | 560                            | 5%               | E24             |
|                                 |     |                                | 10%              | E12             |
| 25                              | 10  | 10 1000                        | 1%               | E96             |
|                                 |     |                                | 2%               | E48             |
|                                 |     |                                | 5%               | E24             |
|                                 |     |                                | 10%              | E12             |
| 16                              | 10  | 1500                           | 1%               | E96             |
|                                 |     | 1470                           | 2%               | E48             |
|                                 |     | 1500                           | 5%               | E24             |
|                                 |     |                                | 10%              | E12             |

Any capacitance value in the capacitance range may be available on request.

- 2. Variants 01, 03 and 08 are not suitable for solder assembly methods. They shall be assembled using glue or wire bond techniques.
- 3. Sn/Pb plating with tin content of 50% minimum and 97% maximum, remainder lead.



PAGE 8

**ISSUE 4** 

#### 1.5 MAXIMUM RATINGS

The maximum ratings shall not be exceeded at any time during use or storage.


Maximum ratings shall only be exceeded during testing to the extent specified in this specification and when stipulated in Test Methods and Procedures of the ESCC Generic Specification.

| Characteristics                | Symbols          | Maximum Ratings      | Units | Remarks                |
|--------------------------------|------------------|----------------------|-------|------------------------|
| Rated Voltage                  | U <sub>R</sub>   | 16, 25, 50, 100, 200 | V     | Note 1                 |
| Operating Temperature<br>Range | T <sub>op</sub>  | -55 to +125          | °C    | Without derating. Tamb |
| Storage Temperature<br>Range   | T <sub>stg</sub> | -55 to +125          | °C    |                        |
| Soldering Temperature          | T <sub>sol</sub> | +260                 | °C    | Note 2                 |

#### NOTES:

- 1. As required; See Para. 1.4.2.
- 2. Duration 10 seconds maximum.

#### 1.6 PHYSICAL DIMENSIONS



| Symbols | Dimensions (mm) |              |       |       |  |  |
|---------|-----------------|--------------|-------|-------|--|--|
|         | Variants 01     | , 03, 06, 08 | Varia | nt 05 |  |  |
|         | Min Max         |              | Min   | Max   |  |  |
| L       | 1.4             | 1.8          | 1.4   | 2.3   |  |  |
| I       | 0.6             | 1            | 0.6   | 1.5   |  |  |
| е       | -               | 1            | -     | 1.5   |  |  |
| М       | 0.1             | 0.5          | 0.1   | 0.5   |  |  |

#### 1.7 FUNCTIONAL DIAGRAM





PAGE 9

**ISSUE 4** 

#### 2 <u>REQUIREMENTS</u>

#### 2.1 <u>GENERAL</u>

The complete requirements for procurement of the components specified herein are as stated in this specification and the ESCC Generic Specification. Permitted deviations from the Generic Specification, applicable to this specification only, are listed below.

Permitted deviations from the Generic Specification and this Detail Specification, formally agreed with specific Manufacturers on the basis that the alternative requirements are equivalent to the ESCC requirement and do not affect the component's reliability, are listed in the appendices attached to this specification.

#### 2.1.1 Deviations from the Generic Specification

#### 2.1.1.1 Deviations from Qualification and Periodic Tests - Chart F4

(a) Solderability: not applicable to Variants 01, 03 and 08.

#### 2.2 <u>MARKING</u>

The marking shall be in accordance with the requirements of ESCC Basic Specification No. 21700 and as follows.

The information to be marked on the component or its primary package shall be:

- (a) The ESCC qualified components symbol (for ESCC qualified components only).
- (b) The ESCC Component Number (see Para. 1.4.1).
- (c) Traceability information.



#### 2.3 <u>ELECTRICAL MEASUREMENTS AT ROOM, HIGH AND LOW TEMPERATURES</u> Electrical measurements shall be performed at room, high and low temperatures.

## 2.3.1 <u>Room Temperature Electrical Measurements</u>

The measurements shall be performed at  $T_{amb}$  = +22 ±3°C.

| Characteristics          | Symbols | Symbols Test Method and Conditions | Tolerance | Lin                  | nits                 | Units |
|--------------------------|---------|------------------------------------|-----------|----------------------|----------------------|-------|
|                          |         |                                    | (±)       | Min                  | Max                  |       |
| Capacitance              | CA      | ESCC No. 3009                      |           |                      |                      | pF    |
|                          |         |                                    | 0.25pF    | C <sub>n</sub> -0.25 | C <sub>n</sub> +0.25 |       |
|                          |         |                                    | 0.5pF     | Cn -0.5              | C <sub>n</sub> +0.5  |       |
|                          |         |                                    | 1pF       | Cn - 1               | Cn +1                |       |
|                          |         |                                    | 1%        | 0.99Cn               | 1.01Cn               |       |
|                          |         |                                    | 2%        | 0.98Cn               | 1.02C <sub>n</sub>   |       |
|                          |         |                                    | 5%        | 0.95Cn               | 1.05Cn               |       |
|                          |         |                                    | 10%       | 0.9Cn                | 1.1Cn                |       |
| Tangent of Loss          | tgδ     | ESCC No. 3009                      | All       |                      |                      |       |
| Angle                    |         | For C <sub>n</sub> < 50pF          |           | -                    | Note 1               |       |
|                          |         | For C <sub>n</sub> ≥ 50pF          |           | -                    | 15 x10⁻⁴             | -     |
| Insulation<br>Resistance | Rı      | ESCC No. 3009                      | All       | 100                  | -                    | GΩ    |
| Voltage Proof            | VP      | ESCC No. 3009                      | All       | 2.5U <sub>R</sub>    | -                    | V     |

## NOTES:

1. For  $C_n < 50pF$ ,  $tg\delta < 1.5 \times (150/C_n + 7) \times 10^{-4}$ , where the unit quantity for  $C_n$  is in pF.

#### 2.3.2 <u>High and Low Temperatures Electrical Measurements</u>

| Characteristics            | Symbols |  |     | nits | Units                |
|----------------------------|---------|--|-----|------|----------------------|
|                            |         | (Note 1)   | Min | Max  |                      |
| Insulation<br>Resistance   | Rı      | ESCC No. 3009<br>T <sub>amb</sub> = +125 ±2°C<br>Note 2                        | 10  | -    | GΩ                   |
| Temperature<br>Coefficient | тс      | ESCC No. 3009<br>T <sub>amb</sub> = -55 ±2°C, +20 ±2°C,<br>+125 ±2°C<br>Note 3 |     |      | 10 <sup>-6</sup> /°C |
|                            |         | For C <sub>n</sub> > 20pF  | -30 | +30  |                      |
|                            |         | For C <sub>n</sub> ≤ 20pF  | Not | te 4 |                      |

#### NOTES:

- 1. The measurements shall be performed on a sample of 5 components from each manufacturing lot with 0 failures allowed. In the event of any failure a 100% inspection may be performed.
- 2. Guaranteed but not tested during Chart F3 of the Generic Specification; only tested in Temperature Characterisation during Chart F4 of the Generic Specification.
- 3. In the case of a 100% inspection, a 1% total percent defective is allowed.
- 4. Temperature Coefficient is not specified for  $C_n \le 20pF$  due to test equipment limitations.



ISSUE 4

#### 2.4 INTERMEDIATE AND END-POINT ELECTRICAL MEASUREMENTS

Unless otherwise specified, the measurements shall be performed at  $T_{amb}$  = +22 ±3°C.

Unless otherwise specified the test methods and test conditions shall be as per the corresponding test defined in Para. 2.3.1 Room Temperature Electrical Measurements.

| Test Reference per ESCC<br>No. 3009 | Characteristics                | Symbols                         | Limits                  |     | Units    |
|-------------------------------------|--------------------------------|---------------------------------|-------------------------|-----|----------|
|                                     |                                |                                 | Min                     | Max |          |
| Mounting                            |                                |                                 |                         |     |          |
| Final Measurements                  | Capacitance                    | CA                              | Record Values<br>Note 1 |     |          |
|                                     | Tangent of Loss Angle          | tgδ                             |                         |     |          |
|                                     | Insulation Resistance          | Rı                              | 100                     | -   | GΩ       |
| Rapid Change of Temperature         |                                |                                 |                         |     |          |
| Initial Measurements                | Capacitance                    | CA                              | Notes 1, 2              |     |          |
| Final Measurements                  | Capacitance                    | CA                              | Note 1                  |     |          |
|                                     | Change in Capacitance          | $\Delta C_A/C_A$                | -1                      | +1  | pF or    |
|                                     |                                |                                 | -1                      | +1  | %        |
|                                     |                                |                                 |                         |     | (Note 3) |
|                                     | Tangent of Loss Angle          | tgδ                             | Note 4                  |     |          |
| Steady State Humidity (85/85)       |                                |                                 |                         |     |          |
| Initial Measurements                | Capacitance                    | CA                              | Note 1                  |     |          |
| Final Measurements<br>(1000 hours)  | Capacitance                    | CA                              | Note 1                  |     |          |
|                                     | Change in Capacitance          | ΔC <sub>A</sub> /C <sub>A</sub> | -1                      | +1  | pF or    |
|                                     |                                |                                 | -2                      | +2  | %        |
|                                     |                                |                                 |                         |     | (Note 3) |
|                                     | Tangent of Loss Angle          | tgδ                             | Note 4                  |     |          |
|                                     | Insulation Resistance (Note 5) | Rı                              | 10                      | -   | GΩ       |



ISSUE 4

| Test Reference per ESCC                             | Characteristics  | Symbols                         | Limits            |     | Units    |
|---|--|---------------------------------|-------------------|-----|----------|
| No. 3009  |  |                                 | Min               | Max |          |
| Operating Life                                      |  |                                 |                   |     |          |
| Initial Measurements                                | Capacitance  | CA                              | Notes 1, 2        |     |          |
| Intermediate Measurements<br>(1000 hours) (Note 6)  | Capacitance  | CA                              | Note 1            |     |          |
|   | Change in Capacitance                                    | $\Delta C_A/C_A$                | -1                | +1  | pF or    |
|   |  |                                 | -3                | +3  | %        |
|   |  |                                 |                   |     | (Note 3) |
|   | Insulation Resistance                                    | Rı                              | 10                | -   | GΩ       |
| Final Measurements<br>(1000 or 2000 hours) (Note 7) | Capacitance  | CA                              | Note 1            |     |          |
|   | Change in Capacitance                                    | ΔC <sub>A</sub> /C <sub>A</sub> | -1                | +1  | pF or    |
|   |  |                                 | -3                | +3  | %        |
|   |  |                                 |                   |     | (Note 3) |
|   | Tangent of Loss Angle                                    | tgδ                             | Note 4            |     |          |
|   | Insulation Resistance                                    | Ri                              | 10                | -   | GΩ       |
|   | Voltage Proof  | VP                              | 2.5U <sub>R</sub> | -   | V        |
| Temperature Characterisation                        | Insulation Resistance at<br>T <sub>amb</sub> = +125 ±2°C | Rı                              | Note 8            |     |          |
|   | Temperature Coefficient                                  | тс                              | Note 8            |     |          |
| Robustness of Terminations                          |  |                                 |                   |     |          |
| Final Measurements                                  | Capacitance  | CA                              | Note 1            |     |          |

#### NOTES:

- 1. As specified in Para. 2.3.1 Room Temperature Electrical Measurements.
- 2. Capacitance values recorded during Mounting may be used as initial measurements.
- 3. Whichever is greater.
- 4. Twice the value specified in Para. 2.3.1 Room Temperature Electrical Measurements.
- 5. Test conditions for Insulation Resistance shall be as specified in Steady State Humidity in the ESCC Generic Specification.
- 6. Intermediate measurements are optional at the Manufacturer's discretion.
- 7. 1000 hours is applicable to Periodic Testing for extension of qualification. 2000 hours is applicable to Qualification Testing, and to Periodic Testing for renewal of qualification after lapse.
- 8. As specified in Para. 2.3.2 High and Low Temperatures Electrical Measurements.

#### 2.5 <u>BURN-IN</u>

The requirements for Burn-in are specified in the ESCC Generic Specification. The following conditions shall also apply:

• After Burn-in, the components shall be removed from the chamber and allowed to cool under normal atmospheric conditions for recovery for 24 hours minimum.