

Page i

# DIODES, MICROWAVE, SILICON, MULTIPLIER VARACTOR, BASED ON TYPES ML4402, ML4404 THRU ML4409 AND ML40721 ESCC Detail Specification No. 5512/001

# ISSUE 1 October 2002





# **ESCC Detail Specification**

PAGE	ii
ISSUE	1

#### **LEGAL DISCLAIMER AND COPYRIGHT**

European Space Agency, Copyright © 2002. All rights reserved.

The European Space Agency disclaims any liability or responsibility, to any person or entity, with respect to any loss or damage caused, or allleged to be caused, directly or indirectly by the use and application of this ESCC publication.

This publication, without the prior permission of the European Space Ageny and provided that it is not used for a commercial purpose, may be:

- copied in whole in any medium without alteration or modification.
- copied in part, in any medium, provided that the ESCC document identification, comprising the ESCC symbol, document number and document issue, is removed.



# european space agency agence spatiale européenne

Pages 1 to 32

# DIODES, MICROWAVE, SILICON, MULTIPLIER VARACTOR, BASED ON TYPES ML4402, ML4404 THRU ML4409 AND ML40721 ESA/SCC Detail Specification No. 5512/001



# space components coordination group

		Approved by			
Issue/Rev.	Date	SCCG Chairman	ESA Director General or his Deputy		
Issue 1	December 1992	Comment	T. tedu		
Revision 'A'	December 1993	To no men's	Lede		
Revision 'B'	August 1995	To mo mice S	Hom		
Revision 'C'	May 2000	Sannot	Hom		



Rev. 'C'

PAGE 2

ISSUE 1

# **DOCUMENTATION CHANGE NOTICE**

Rev. Letter	Rev. Date	Reference	CHANGE Item	Approved DCR No.
'A'	Dec '93	P8. Table 1(a) P9. Table 1(b) P19. Figure 2(o) P22. Para. 4.3.2 Para. 4.3.3 P23. Para. 4.4.2 P25. Table 2 P26. Table 2 a.c. Table 3 Table 4 P28. Table 5(b)	<ul> <li>Type ML40721 added</li> <li>'Type Variant' changed to 'Type Variants'</li> <li>Type ML40721 added</li> <li>Variant 92 added</li> <li>Items 1 and 2 amended</li> <li>Variant 92 added</li> <li>Table standardised</li> <li>Table standardised</li> <li>Variant 92 added</li> <li>Variant 92 added</li> <li>Table standardised</li> <li>Table standardised</li> <li>Table standardised</li> <li>Variant 92 added</li> <li>Variant 92 added</li> <li>Variant 92 added</li> <li>Variant 92 added</li> </ul>	221079 None 22613 221079 221079 221079 221079 221079 221079 221079 23613 221079 23613 221079 23613 221079 23613 221079 23613
'B'	Aug. '95	P1. Cover Page P2. DCN P26. Table 2	: Unit for Variants 76 to 86 moved to 87 to 91	None None 23741
'C'	May '00	P1. Cover Page P2. DCN P4. T of C  P21. Para. 4.2.1  Para. 4.2.2  Para. 4.2.3  P24. Para. 4.7  P26. Table 4  P28. Table 5(b)  Table 5(c)  P29. Para. 4.8.3	<ul> <li>Table 5(b) entry amended</li> <li>Table 5(c) entry amended</li> <li>Deviations (a) and (b) paragraph reference amended</li> <li>Deviation (c) deleted</li> <li>Deviation (a) paragraph reference amended</li> <li>Deviation (a) paragraph reference amended</li> <li>Category amended</li> <li>In Note 1, " = Δ3" deleted</li> <li>Title amended</li> <li>Table deleted</li> <li>In the second sentence, "5(c)" amended to "5(b)"</li> </ul>	None None 221552 221552 221552 221552 221552 221552 221552 221552 221552 221552 221552 221552



PAGE 3

ISSUE 1

# **TABLE OF CONTENTS**

1.	GENERAL	Page 5
••	GENERAL	5
1.1	Scope	5
1.2	Type Variants	5
1.3	Maximum Ratings	5
1.4	Parameter Derating Information	5
1.5	Physical Dimensions	5
1.6	Functional Diagram	5
1.7	Handling Precautions	5 5 5 5 5
2.	APPLICABLE DOCUMENTS	5
3.	TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS	5
4.	REQUIREMENTS	21
4.1	General	21
4.2	Deviations from Generic Specification	21
4.2.1	Deviations from Special In-process Controls	21
4.2.2	Deviations from Final Production Tests	21
4.2.3	Deviations from Burn-in and Electrical Measurements	21
4.2.4	Deviations from Qualification Tests	21
4.2.5	Deviations from Lot Acceptance Tests	21
4.3	Mechanical and Environmental Requirements	21
4.3.1	Dimension Check	21
4.3.2	Weight	22
4.3.3	Terminal Strength	22 22
4.4	Materials and Finishes	23
4.4.1	Case	23
4.4.2	Lead Materials and Finish	23
4.5	Marking	23
4.5.1	General	23
4.5.2	Cathode Identification	23
4.5.3	The SCC Component Number	24
4.5.4	Traceability Information	24
4.6	Electrical Measurements	24
4.6.1	Electrical Measurements at Room Temperature	24
4.6.2	Electrical Measurements at High and Low Temperatures	24
4.6.3	Circuits for Electrical Measurements	24
4.7	Burn-in Tests	24
4.7.1	Parameter Drift Values	24
4.7.2	Conditions for High Temperature Reverse Bias Burn-in	24 24
4.7.3	Conditions for Power Burn-in	24
4.7.4	Electrical Circuits for High Temperature Reverse Bias and Power Burn-in	24
4.8	Environmental and Endurance Tests	29
4.8.1	Electrical Measurements on Completion of Environmental Tests	29
4.8.2	Electrical Measurements at Intermediate Points and on Completion of Endurance Tests	29
4.8.3	Conditions for Operating Life Tests	29 29
4.8.4	Electrical Circuits for Operating Life Tests	29 29
4.9	Total Dose Irradiation Testing	29
4.9.1	Application	29 29
4.9.2	Bias Conditions	29 29
4.9.3	Electrical Measurements	29 29
4.10	Special Testing	29 29
-	·	23



Rev. 'C'

PAGE 4

ISSUE 1

TABLE	<u>:S</u>	<u>Page</u>
1(a) 1(b)	Type Variants Maximum Ratings	6 9
2 ′	Electrical Measurements at Room Temperature - D.C. Parameters	25
	Electrical Measurements at Room Temperature - A.C. Parameters	26
3 4	Electrical Measurements at High and Low Temperatures Parameter Drift Values	26 26
5(a)	Conditions for High Temperature Reverse Bias Burn-in	28
5(b)	Conditions for Power Burn-in and Operating Life Tests	28
6 7	Electrical Measurements at Intermediate Points and on Completion of Endurance Testing Electrical Measurements During and on Completion of Irradiation Testing	30 31
FIGUR	<u>ES</u>	
1	Parameter Derating Information	10
2	Physical Dimensions	11
3	Functional Diagram	20
4	Circuits for Electrical Measurements	27
5(a)	Electrical Circuit for High Temperature Reverse Bias Burn-in	28
5(b)	Electrical Circuit for Power Burn-in and Operating Life Tests	28
6	Bias Conditions for Irradiation Testing	30
APPEN	IDICES (Applicable to specific Manufacturers only)	
'A'	Agreed deviations for M/A-Com Ltd. (G.B.)	32



Rev. 'A'

PAGE

ISSUE 1

5

#### 1. **GENERAL**

#### 1.1 SCOPE

This specification details the ratings, physical and electrical characteristics, test and inspection data for a Diode, Microwave, Silicon, Multiplier Varactor, based on Types ML4402, ML4404 thru ML4409 and ML40721. It shall be read in conjunction with ESA/SCC Generic Specification No. 5010, the requirements of which are supplemented herein.

#### 1.2 TYPE VARIANTS

Variants of the basic diodes specified herein, which are also covered by this specification are given in Table 1(a).

#### 1.3 MAXIMUM RATINGS

The maximum ratings, which shall not be exceeded at any time during use or storage, applicable to the diodes specified herein, are as scheduled in Table 1(b).

#### 1.4 PARAMETER DERATING INFORMATION

The derating information applicable to the diodes specified herein is shown in Figure 1.

#### 1.5 PHYSICAL DIMENSIONS

The physical dimensions of the diodes specified herein are shown in Figure 2.

#### 1.6 FUNCTIONAL DIAGRAM

The functional diagram, showing lead identification, of the diodes specified herein, is shown in Figure 3.

#### 1.7 HANDLING PRECAUTIONS

These devices are susceptible to damage by electrostatic discharge. Therefore, suitable precautions shall be employed for protection during all phases of manufacture, testing, packaging, shipment and any handling.

These components are Categorised as Class 2 with a Minimum Critical Path Failure Voltage of 3000V.

#### 2. APPLICABLE DOCUMENTS

The following documents form part of this specification and shall be read in conjunction with it:

(a) ESA/SCC Generic Specification No. 5010 for Discrete Microwave Semiconductor Components.

# 3. TERMS, DEFINITIONS, ABBREVIATIONS, SYMBOLS AND UNITS

For the purpose of this specification, the terms, definitions, abbreviations, symbols and units specified in ESA/SCC Basic Specification No. 21300 shall apply.



PAGE 6

ISSUE 1

# TABLE 1(a) - TYPE VARIANTS

VARIANT (1)	(2) BASED ON TYPE	(3) FIGURE	TOTAL CAPACITANCE		CAPAC	(5) CTION ITANCE (pF)	(6) BODY-LID AND LEAD MATERIAL AND FINISH
			MIN	MAX	MIN	MAX	7.1.1.2.1.1.1.1.1.1
01	ML4402 - 30	2(a)	0.40	0.65	0.2	0.45	A7-D2
02	ML4402 - 31	2(b)	0.40	0.65	0.2	0.45	A7-D2
03	ML4402 - 32	2(c)	0.51	0.76	0.2	0.45	A7-D2
04	ML4402 - 34	2(d)	0.60	0.85	0.2	0.45	A7-D2
05	ML4402 - 43	2(e)	1.00	1.25	0.2	0.45	A7-D2
06	ML4402 - 56	2(f)	0.73	0.98	0.2	0.45	A7-D2
07	ML4402 - 91	2(g)	0.51	0.76	0.2	0.45	A7-D2
08	ML4402 - 92	2(h)	0.51	0.76	0.2	0.45	A7-D2
09	ML4402 - 96	2(i)	0.38	0.63	0.2	0.45	A7-D2
10	ML4402 - 97	2(j)	0.38	0.63	0.2	0.45	A7-D2
11	ML4402 - 111	2(k)	0.51	0.76	0.2	0.45	A7-D2
12	ML4402 - 120	2(1)	0.36	0.61	0.2	0.45	D2
13	ML4402 - 148	2(m)	0.31	0.56	0.2	0.45	A7
14	ML4402 - 144B	2(n)	0.74	0.99	0.2	0.45	D2
15	ML4402 - 186	2(0)	0.35	0.60	0.2	0.45	D2
16	ML4404 - 30	2(a)	0.40	0.65	0.2	0.45	A7-D2
17	ML4404 - 31	2(b)	0.40	0.65	0.2	0.45	A7-D2
18	ML4404 - 32	2(c)	0.51	0.76	0.2	0.45	A7-D2
19	ML4404 - 34	2(d)	0.60	0.85	0.2	0.45	A7-D2
20	ML4404 - 43	2(e)	1.00	1.25	0.2	0.45	A7-D2
21	ML4404 - 56	2(f)	0.73	0.98	0.2	0.45	A7-D2
22	ML4404 - 91	2(g)	0.51	0.76	0.2	0.45	A7-D2
23	ML4404 - 92	2(h)	0.51	0.76	0.2	0.45	A7-D2
24	ML4404 - 96	2(i)	0.38	0.63	0.2	0.45	A7-D2
25	ML4404 - 97	2(j)	0.38	0.63	0.2	0.45	A7-D2
26	ML4404 - 111	2(k)	0.51	0.76	0.2	0.45	A7-D2
27	ML4404 - 120	2(l)	0.36	0.61	0.2	0.45	D2
28	ML4404 - 148	2(m)	0.31	0.56	0.2	0.45	A7
29	ML4404 - 144B	2(n)	0.74	0.99	0.2	0.45	D2
30	ML4404 - 186	2(0)	0.35	0.60	0.2	0.45	D2
31	ML4405 - 30	2(a)	0.60	1.00	0.4	0.8	A7-D2
32	ML4405 - 31	2(b)	0.60	1.00	0.4	0.8	A7-D2
33	ML4405 - 32	2(c)	0.71	1.11	0.4	0.8	A7-D2
34	ML4405 - 34	2(d)	0.80	1.20	0.4	0.8	A7-D2
35	ML4405 - 43	2(e)	1.20	1.60	0.4	0.8	A7-D2
36	ML4405 - 56	2(f)	0.93	1.33	0.4	0.8	A7-D2



PAGE 7

ISSUE 1

# TABLE 1(a) - TYPE VARIANTS (CONT'D)

VARIANT (1)	(2) BASED ON TYPE	(3) FIGURE	TOTAL CAPA C <sub>T</sub> (		CAPAC	(5) CTION ITANCE (pF)	(6) BODY-LID AND LEAD MATERIAL AND FINISH
			MIN	MAX	MIN	MAX	7 IIVIOIT
37	ML4405 - 91	2(g)	0.71	1.11	0.4	0.8	A7-D2
38	ML4405 - 92	2(h)	0.71	1.11	0.4	0.8	A7-D2
39	ML4405 - 96	2(i)	0.58	0.98	0.4	0.8	A7-D2
40	ML4405 - 97	2(j)	0.58	0.98	0.4	0.8	A7-D2
41	ML4405 - 111	2(k)	0.71	1.11	0.4	0.8	A7-D2
42	ML4405 - 120	2(1)	0.56	0.96	0.4	0.8	D2
43	ML4405 - 148	2(m)	0.69	1.09	0.4	0.8	<b>A</b> 7
44	ML4405 - 144B	2(n)	0.94	1.34	0.4	0.8	D2
45	ML4405 - 186	2(0)	0.55	0.95	0.4	0.8	D2
46	ML4406 - 30	2(a)	0.90	1.40	0.7	1.2	A7-D2
47	ML4406 - 31	2(b)	0.90	1.40	0.7	1.2	A7-D2
48	ML4406 - 32	2(c)	1.01	1.51	0.7	1.2	A7-D2
49	ML4406 - 34	2(d)	1.10	1.60	0.7	1.2	A7-D2
50	ML4406 - 43	2(e)	1.50	2.00	0.7	1.2	A7-D2
51	ML4406 - 56	2(f)	1.23	1.73	0.7	1.2	A7-D2
52	ML4406 - 91	2(g)	1.01	1.51	0.7	1.2	A7-D2
53	ML4406 - 92	2(h)	1.01	1.51	0.7	1.2	A7-D2
54	ML4406 - 96	2(i)	0.88	1.38	0.7	1.2	A7-D2
55	ML4406 - 97	2(j)	0.88	1.38	0.7	1.2	A7-D2
56	ML4406 - 111	2(k)	1.01	1.51	0.7	1.2	A7-D2
57	ML4406 - 120	2(l)	0.86	1.36	0.7	1.2	D2
58	ML4406 - 148	2(m)	0.99	1.49	0.7	1.2	A7
59	ML4406 - 144B	2(n)	1.24	1.74	0.7	1.2	D2
60	ML4406 - 186	2(o)	0.85	1.35	0.7	1.2	D2
61	ML4407 - 30	2(a)	1.20	2.70	1.0	2.5	A7-D2
62	ML4407 - 31	2(b)	1.20	2.70	1.0	2.5	A7-D2
63	ML4407 - 32	2(c)	1.31	2.81	1.0	2.5	A7-D2
64	ML4407 - 34	2(d)	1.40	2.90	1.0	2.5	A7-D2
65	ML4407 - 43	2(e)	1.80	3.30	1.0	2.5	A7-D2
66	ML4407 - 56	2(f)	1.53	3.03	1.0	2.5	A7-D2
67	ML4407 - 91	2(g)	1.31	2.81	1.0	2.5	A7-D2
68	ML4407 - 92	2(h)	1.31	2.81	1.0	2.5	A7-D2
69	ML4407 - 96	2(i)	1.18	2.68	1.0	2.5	A7-D2
70	ML4407 - 97	2(j)	1.18	2.68	1.0	2.5	A7-D2
71	ML4407 - 111	2(k)	1.31	2.81	1.0	2.5	A7-D2



Rev. 'A'

PAGE 8

ISSUE 1

# TABLE 1(a) - TYPE VARIANTS (CONT'D)

VARIANT (1)	(2) BASED ON TYPE	(3) FIGURE	(4) TOTAL CAPACITANCE C <sub>T</sub> (pF)		JUNC CAPAC C <sub>J</sub>	TANCE	(6) BODY-LID AND LEAD MATERIAL AND FINISH
			MIN	MAX	MIN	MAX	ANDTINION
72	ML4407 - 120	2(l)	1.16	2.66	1.0	2.5	D2
73	ML4407 - 148	2(m)	1.29	2.79	1.0	2.5	A7
74	ML4407 - 144B	2(n)	1.54	3.04	1.0	2.5	D2
75	ML4407 - 186	2(0)	1.15	2.65	1.0	2.5	D2
76	ML4408 - 30	2(a)	2.20	4.20	2.0	4.0	A7-D2
77	ML4408 - 31	2(b)	2.20	4.20	2.0	4.0	A7-D2
78	ML4408 - 32	2(c)	2.31	4.31	2.0	4.0	A7-D2
79	ML4408 - 34	2(d)	2.40	4.40	2.0	4.0	A7-D2
80	ML4408 - 43	2(e)	2.80	4.80	2.0	4.0	A7-D2
81	ML4408 - 56	2(f)	2.53	4.53	2.0	4.0	A7-D2
82	ML4408 - 91	2(g)	2.31	4.31	2.0	4.0	A7-D2
83	ML4408 - 92	2(h)	2.31	4.31	2.0	4.0	A7-D2
84	ML4408 - 111	2(k)	2.31	4.31	2.0	4.0	A7-D2
85	ML4408 - 148	2(m)	2.29	4.29	2.0	4.0	A7
86	ML4408 - 144B	2(n)	2.54	4.54	2.0	4.0	D2
87	ML4409 - 34	2(d)	3.90	8.40	3.5	8.0	A7-D2
88	ML4409 - 43	2(e)	4.30	8.80	3.5	8.0	A7-D2
89	ML4409 - 56	2(f)	4.03	8.53	3.5	8.0	A7-D2
90	ML4409 - 101	2(p)	4.00	8.50	3.5	8.0	A7-D2
91	ML4409 - 144B	2(n)	4.04	8.54	3.5	8.0	D2
92	ML40721 - 186	2(0)	1.15	2.65	1.0	2.5	D2



Rev. 'A'

PAGE

ISSUE 1

# TABLE 1(b) - MAXIMUM RATINGS

No.	CHARACTERISTIC	SYMBOL	MAXIMUM RATINGS	UNIT	REMARKS
1	D.C. Reverse Voltage Variants 01 to 30 Variants 31 to 45 Variants 46 to 60 Variants 61 to 75 and 92 Variants 76 to 86 Variants 87 to 91	V <sub>R</sub>	- 15 - 20 - 30 - 45 - 60 - 75	V	Note 1
2	D.C. Forward Current (Continuous) Variants 01 to 30 Variants 31 to 86 and 92 Variants 87 to 91	lε	200 300 500	mA	Note 1
3	R.F. Power Dissipation Variants 01 to 14 and 16 to 29 Variants 15 and 30 Variants 31 to 44 Variants 45, 60, 75 and 92 Variants 46 to 59 Variants 61 to 74 Variants 76 to 86 Variants 87 to 91	P <sub>tot</sub>	2.0 0.5 2.8 0.6 3.6 4.2 5.0 0.7	W	Note 1
4	Operating Temperature Range	T <sub>op</sub>	-65 to +150	°C	T <sub>case</sub>
5	Storage Temperature Range	T <sub>stg</sub>	-65 to +150	°C	
6	Soldering Temperature	T <sub>sol</sub>	+ 230	°C	Note 2

#### <u>NOTES</u>


- 1. At  $T_{case} = +25$ °C. For derating at  $T_{case} > +25$ °C, see Figure 1.
- 2. Duration 5 seconds maximum (at a distance of not less than 1.5mm from the body for Variants 14, 15, 29, 30, 44, 45, 59, 60, 74, 75, 86 and 91) and the same termination shall not be resoldered until 3 minutes have elapsed.





PAGE 10

ISSUE 1

# **FIGURE 1 - PARAMETER DERATING INFORMATION**










PAGE 11

ISSUE 1


# **FIGURE 2 - PHYSICAL DIMENSIONS**

# FIGURE 2(a) - VARIANTS 01, 16, 31, 46, 61, 76




	<b>←</b> L →	<b>←</b> —B—	<del>-&gt; </del>	
		->	B1 <b>←</b>	
ØD1 Ød	B2	• • •		   ØD
	<del></del>	Cathode end	>	


SYMBOL	MILLIMETRES		
STIVIBOL	MIN	MAX	
Α	5.20	5.72	
В	2.16	2.46	
B1	0.41	0.61	
B2	0.15	0.25	
Ød	1.52	1.63	
ØD	3.00	3.23	
ØD1	1.95	2.11	
L	1.52	1.63	




# FIGURE 2(b) - VARIANTS 02, 17, 32, 47, 62, 77



SYMBOL	MILLIM	IETRES
STINIBOL	MIN	MAX
Α	2.16	2.46
B1	0.41	0.61
B2	0.15	0.25
ØD	3.00	3.23
ØD1	1.95	2.11








PAGE 12


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)


FIGURE 2(c) - VARIANTS 03, 18, 33, 48, 63, 78




SYMBOL	MILLIMETRES	
STWIDOL	MIN	MAX
Α	1.37	1.68
B1	0.41	0.61
B2	0.15	0.20
ØD	3.00	3.23
ØD1	1.95	2.11



# FIGURE 2(d) - VARIANTS 04, 19, 34, 49, 64, 79, 87



SYMBOL	WILLIME I RES	
O I WIDOL	MIN	MAX
Α	19.45	20.12
B1	2.54	-
B2	0.53	0.83
B3	0.19	0.41
Ød	2.33	2.44
ØD	-	6.10
ØD1	5.20	5.46
L	4.57	4.83






PAGE 13


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

FIGURE 2(e) - VARIANTS 05, 20, 35, 50, 65, 80, 88



SYMBOL	MILLIMETRES	
STWIDOL	MIN	MAX
Α	11.18	11.68
В	3.02	3.66
B1	0.64	0.89
B2	0.18	0.23
B3	1.17	1.27
С	6.50	7.90
ØD	6.48	6.73
ØD1	5.20	5.50
ØD2	4.80	5.20
ØD3	2.00	2.70
V	0.76	1.02



#### **NOTES**

- 1. Spline socket to fit S-072 Bristol spline key 1.78mm deep.
- 2. 0.51mm x 45°.




PAGE 14


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)


FIGURE 2(f) - VARIANTS 06, 21, 36, 51, 66, 81, 89




SYMBOL	MILLIMETRES	
OTIVIBOL	MIN	MAX
Α	19.46	20.12
B1	-	0.76
B2	3.00	3.60
B3	2.41	2.67
B4	3.68	3.94
Ød	2.33	2.39
ØD	-	6.10
ØD1	4.72	4.83
ØD2	3.81	4.19
L	4.57	4.83




# FIGURE 2(g) - VARIANTS 07, 22, 37, 52, 67, 82



SYMBOL	MILLIMETRES	
OTWIDOL	MIN	MAX
Α	2.92	3.28
В	1.40	1.65
B1	0.41	0.61
B2	0.15	0.20
Ød	1.52	1.63
ØD	3.00	3.23
ØD1	1.95	2.11
ØD2	1.85	2.03
L	1.52	1.63








PAGE 15


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

# FIGURE 2(h) - VARIANTS 08, 23, 38, 53, 68, 83



SYMBOL	MILLIMETRES	
STIVIDOL	MIN	MAX
Α	4.42	4.93
В	1.40	1.65
B1	0.41	0.61
B2	0.15	0.20
Ød	1.52	1.63
ØD	3.00	3.23
ØD1	1.95	2.11
L	1.52	1.63









FIGURE 2(i) - VARIANTS 09, 24, 39, 54, 69



SYMBOL	MILLIMETRES	
STWIDOL	MIN	MAX
Α	1.78	2.03
В	1.02	1.27
B1	-	0.38
B2	0.10	0.25
Ød	0.61	0.66
ØD	1.98	2.18
ØD1	1.19	1.35








PAGE 16


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

# FIGURE 2(j) - VARIANTS 10, 25, 40, 55, 70



	•	
SYMBOL	MILLIMETRES	
STIVIBUL	MIN	MAX
Α	2.54	2.79
В	1.02	1.27
B1	-	0.38
B2	0.10	0.25
Ød	0.61	0.66
ØD	1.98	2.18
ØD1	1.19	1.35








FIGURE 2(k) - VARIANTS 11, 26, 41, 56, 71, 84



SYMBOL	MILLIMETRES	
STIVIBOL	MIN	MAX
Α	4.71	5.30
В	1.47	1.80
B1	0.41	0.61
B2	0.20	0.30
С	1.50	2.80
C1	0.38	0.64
ØD	3.00	3.23
ØD1	2.49	2.59
ØD2	0.90	2.20
Q	0.76	1.02
V	0.11	2.33







PAGE 17

ISSUE 1


# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

# FIGURE 2(I) - VARIANTS 12, 27, 42, 57, 72







SYMBOL	MILLIMETRES	
	MIN	MAX
Α	1.02	1.27
B1	0.23	0.33
B2	0.10	0.15
ØD	1.29	1.40



# FIGURE 2(m) - VARIANTS 13, 28, 43, 58, 73, 85



SYMBOL	MILLIMETRES	
STIVIDOL	MIN	MAX
Α	4.24	4.75
В	1.02	1.32
B1	0.20	0.30
B2	0.46	0.56
С	2.74	3.65
C1	0.38	0.64
Ød	1.22	1.32
ØD	2.87	3.00
ØD1	1.60	2.00
Q	0.89	1.14
V	0.64	0.89






PAGE 18


ISSUE 1


# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

FIGURE 2(n) - VARIANTS 14, 29, 44, 59, 74, 86, 91



SYMBOL	MILLIMETRES	
STMBOL	MIN	MAX
В	3.94	4.19
d	0.07	0.25
d1	0.50	1.30
Ød	0.25	0.40
E	10.16	10.67
E1	4.95	5.46
Øg	2.34	2.54
G	6.10	6.60
Н	3.05	3.30
H1	1.12	1.92
J1	1.91	2.16
L	2.00	-
L1	0.10	1.00
L2	1.00	-








Rev. 'A'

PAGE 19


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

FIGURE 2(o) - VARIANTS 15, 30, 45, 60, 75, 92



SYMBOL	MILLIMETRES		
STIVIBOL	MIN	MAX	
В	2.39	2.62	
d	0.07	0.15	
d1	0.48	0.56	
Е	0.79	1.12	
E1	0.10	0.18	
L	3.30	5.84	
S	0.10	-	






PAGE 20


ISSUE 1

# FIGURE 2 - PHYSICAL DIMENSIONS (CONTINUED)

# FIGURE 2(p) - VARIANT 90



SYMBOL	MILLIM	ETRES
OTWIDOL	MIN	MAX
Α	5.34	5.74
В	2.52	2.72
B1	0.61	0.81
B2	0.65	0.85
C	1.68	2.58
ØD	4.03	4.09
ØD1	3.05	3.25
ØD2	1.60	2.00
V	0.64	0.94



# **FIGURE 3 - FUNCTIONAL DIAGRAM**



- 1. Anode
- 2. Cathode

#### **NOTES**

- 1. The cathode end shall be marked with a black dot or band. The marking will not be on the cathode connection but adjacent to it.
- 2. The cathode shall be marked with a black dot.



Rev. 'C'

PAGE 21

ISSUE 1

#### 4. **REQUIREMENTS**

#### 4.1 GENERAL

The complete requirements for procurement of the diodes specified herein shall be as stated in this specification and ESA/SCC Generic Specification No. 5010 for Discrete Microwave Semiconductor Components. Deviations from the Generic Specification applicable to this specification only, are listed in Para. 4.2.

Deviations from the applicable Generic Specification and this Detail Specification, formally agreed with specific Manufacturers on the basis that the alternative requirements are equivalent to the ESA/SCC requirements and do not affect the components' reliability, are listed in the appendices attached to this specification.

#### 4.2 <u>DEVIATIONS FROM GENERIC SPECIFICATION</u>

# 4.2.1 <u>Deviations from Special In-process Controls</u>

- (a) Para. 5.2.3, Total Dose Irradiation Testing: Shall be performed during qualification and extension of qualification.
- (b) Para. 5.2.3, Total Dose Irradiation Testing: Shall be performed during procurement on a lot acceptance basis at the total dose irradiation level specified in the purchase order.

#### 4.2.2 <u>Deviations from Final Production Tests</u> (Chart II)

- (a) Para. 6.3, Pre-burn-in: Shall be performed in accordance with Para. 9.21(a).
- (b) Para. 9.2.2, Die Shear: Shall not be performed for Variants 14, 29, 44, 59, 74, 86 and 91 and no additional thermal tests shall be performed to replace this test.

# 4.2.3 <u>Deviations from Burn-in and Electrical Measurements (Chart III)</u>

(a) Para. 9.21, High Temperature Reverse Bias Burn-in: Shall be performed at 50% of rated V<sub>R</sub>.

#### 4.2.4 <u>Deviations from Qualification Tests</u> (Chart IV)

- (a) Para. 9.2.4, Die Shear: Shall not be performed for Variants 14, 29, 44, 59, 74, 86 and 91 for which thermal resistance measurements shall be performed in accordance with Table 2 of this specification.
- (b) Para. 9.23, Special Testing: Shall not be performed.

#### 4.2.5 <u>Deviations from Lot Acceptance Tests (Chart V)</u>

(a) Para. 9.23, Special Testing: Shall not be performed.

# 4.3 <u>MECHANICAL AND ENVIRONMENTAL REQUIREMENTS</u>

#### 4.3.1 <u>Dimension Check</u>

The dimensions of the diodes specified herein shall be checked. They shall conform to those shown in Figure 2.



Rev. 'A'

PAGE 22

ISSUE 1

# 4.3.2 Weight

The maximum weight of the diodes specified herein shall be:

Variant No.	Weight (g)
01, 16, 31, 46, 61, 76	0.12
02, 17, 32, 47, 62, 77	0.06
03, 18, 33, 48, 63, 78	0.08
04, 19, 34, 49, 64, 79, 87	2.14
05, 20, 35, 50, 65, 80, 88	1.10
06, 21, 36, 51, 66, 81, 89	1.80
07, 22, 37, 52, 67, 82	0.11
08, 23, 38, 53, 68, 83	0.13

Variant No.	Weight (g)
09, 24, 39, 54, 69	0.015
10, 25, 40, 55, 70	0.022
11, 26, 41, 56, 71, 84	0.14
12, 27, 42, 57, 72	0.014
13, 28, 43, 58, 73, 85	0.15
14, 29, 44, 59, 74, 86, 91	0.99
15, 30, 45, 60, 75, 92	0.06
90	0.24

#### 4.3.3 Terminal Strength

The requirements for terminal strength testing are specified in Section 9 of ESA/SCC Generic Specification No. 5010. The test conditions shall be as follows:-

# (a) Condition: 'A' (Tension)

Variants 14, 15, 29, 30, 44, 45, 59, 60, 74, 75, 86, 91 and 92:

- Force: 5.1N.

- Duration: 5 seconds.

#### (b) Condition: 'D2' (Stud Torque)

Variants 05, 20, 35, 50, 65, 80 and 88:

- Torque: 70mNm.

Duration: 5 seconds.

Variants 11, 26, 41, 56, 71, 84 and 90:

Torque: 56mNm.

- Duration: 5 seconds.

Variants 13, 28, 43, 58, 73 and 85:

Torque: 42mNm.

- Duration: 5 seconds.

#### (c) Condition: Compression

Variants 01, 02, 03, 04, 05, 06, 07, 08, 11, 16, 17, 18, 19, 20, 21, 22, 23, 26, 31, 32, 33, 34, 35, 36, 37, 38, 41, 46, 47, 48, 49, 50, 51, 52, 53, 56, 61, 62, 63, 64, 65, 66, 67, 68, 71, 76, 77, 78, 79, 80, 81, 82, 83, 84, 87, 88, 89 and 90:

- Force: 50N.

Duration: 5 seconds.



Rev. 'A'

PAGE 23

ISSUE 1

Variants 09, 10, 12, 13, 24, 25, 27, 28, 39, 40, 42, 43, 54, 55, 57, 58, 69, 70, 72, 73 and 85:

Force: 10N.

Duration: 5 seconds.

The compression test shall be performed by applying the specified force to the end-cap by means of a suitable weight applied for the specified time. On completion of the test, a visual examination shall be performed to check for damage to the end-cap or the ceramic body.

#### 4.4 MATERIALS AND FINISHES

The materials and finishes shall be as specified herein. Where a definite material is not specified, a material which will enable the diodes specified herein to meet the performance requirements of this specification shall be used. Acceptance or approval of any constituent material shall not guarantee acceptance of the finished product.

#### 4.4.1 <u>Case</u>

The case shall be hermetically sealed and have a ceramic body. The lid shall be welded or preform soldered.

#### 4.4.2 Lead Materials and Finish

- (a) For Variants 01, 02, 03, 04, 05, 06, 07, 08, 09, 10, 11, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 26, 31, 32, 33, 34, 35, 36, 37, 38, 39, 40, 41, 46, 47, 48, 49, 50, 51, 52, 53, 54, 55, 56, 61, 62, 63, 64, 65, 66, 67, 68, 69, 70, 71, 76, 77, 78, 79, 80, 81, 82, 83, 84, 87, 88, 89 and 90, the body material shall be Type 'A' with Type '7' finish and the lid material shall be Type 'D' with Type '2' finish, in accordance with the requirements of ESA/SCC Basic Specification No. 23500.
- (b) For Variants 13, 28, 43, 58, 73 and 85, the lead material shall be Type 'A' with Type '7' finish in accordance with the requirements of ESA/SCC Basic Specification No. 23500.
- (c) For Variants 12, 14, 15, 27, 29, 30, 42, 44, 45, 57, 59, 60, 72, 74, 75, 86, 91 and 92, the lead material shall be Type 'D' with Type '2' finish in accordance with the requirements of ESA/SCC Basic Specification No. 23500.

#### 4.5 MARKING

#### 4.5.1 General

The marking of components delivered to this specification shall be in accordance with the requirements of ESA/SCC Basic Specification No. 21700 and the following paragraphs. When the component is too small to accommodate all of the marking specified, as much as space permits shall be marked and the marking information, in full, shall accompany the component in its primary package.

The information to be marked and the order of precedence, shall be as follows:-

- (a) Cathode Identification.
- (b) The SCC Component Number.
- (c) Traceability Information.

#### 4.5.2 Cathode Identification

Cathode identification shall be as shown in Figures 2 and 3 of this specification.



Rev. 'C'

EE4000404DE

PAGE 24

ISSUE 1

#### 4.5.3 The SCC Component Number

Each component shall bear the SCC Component Number which shall be constituted and marked as follows:

	551200101BF
Detail Specification Number	
Type Variant (see Table 1(a))	
Testing Level (B or C, as applicable)	
Total Dose Irradiation Level (if applicable)	

The Total Dose Irradiation Level designation shall be added for those devices for which a sample has been successfully tested to the level in question. For these devices, a code letter shall be added in accordance with the requirements of ESA/SCC Basic Specification No. 22900.

#### 4.5.4 <u>Traceability Information</u>

Each component shall be marked in respect of traceability information as defined in ESA/SCC Basic Specification No. 21700.

#### 4.6 ELECTRICAL MEASUREMENTS

#### 4.6.1 <u>Electrical Measurements at Room Temperature</u>

The parameters to be measured at room temperature are scheduled in Table 2. Unless otherwise specified, the measurements shall be performed at  $T_{amb} = +22 \pm 3$  °C.

#### 4.6.2 <u>Electrical Measurements at High and Low Temperatures</u>

The parameters to be measured at high and low temperatures are scheduled in Table 3. Unless otherwise specified, the measurements shall be performed at +150(+0-3) °C.

#### 4.6.3 <u>Circuits for Electrical Measurements</u>

Circuits for use in performing electrical measurements listed in Table 2 of this specification are shown in Figure 4.

#### 4.7 BURN-IN TESTS

Burn-in shall be Category 2 of Chart III(a).

#### 4.7.1 Parameter Drift Values

The parameter drift values applicable to burn-in are specified in Table 4 of this specification. Unless otherwise stated, the measurements shall be performed at  $T_{amb}$  = +22±3 °C. The parameter drift values ( $\Delta$ ) applicable to the scheduled parameters shall not be exceeded. In addition to these drift value requirements for a given parameter, the appropriate limit value specified in Table 2 shall not be exceeded.

#### 4.7.2 Conditions for High Temperature Reverse Bias Burn-in

The requirements for the high temperature reverse bias burn-in are specified in Section 7 of ESA/SCC Generic Specification No. 5010. The conditions for high temperature reverse bias burn-in shall be as specified in Table 5(a) of this specification.

#### 4.7.3 Conditions for Power Burn-in

The requirements for power burn-in are specified in Section 7 of ESA/SCC Generic Specification No. 5010. The conditions for power burn-in shall be as specified in Table 5(b) of this specification.

# 4.7.4 <u>Electrical Circuits for High Temperature Reverse Bias and Power Burn-in</u>

Circuits for use in performing the H.T.R.B and power burn-in tests are shown in Figures 5(a) and 5(b) of this specification.



Rev. 'A'

PAGE 25

ISSUE 1

# TABLE 2 - ELECTRICAL MEASUREMENTS AT ROOM TEMPERATURE - D.C. PARAMETERS

No.	CHARACTERISTICS	SYMBOL	MIL-STD-750	) TEST CONDITIONS	LIMITS		UNIT
	OF WALL OF LITTLE FIRST	OTWIDOL	TEST METHOD	1231 GONDITIONS	MIN.	MAX.	ONT
1	Reverse Current 1	l <sub>R1</sub>	4016	V <sub>R</sub> = Note 1	-	10	μA
2	Reverse Current 2	I <sub>R2</sub>	4016	V <sub>R</sub> = Note 2	_	50	nA
3	Forward Voltage	V <sub>F</sub>	4011	I <sub>F</sub> = 100mA Variants 01 to 45 Variants 46 to 86 and 92 Variants 87 to 91	- - -	1.3 1.2 1.0	V
4	Thermal Resistance	R <sub>TH(J-C)</sub>	3101	I <sub>F</sub> = 1.0A Note 3 Variants 01 to 14 and 16 to 29 Variants 15 and 30 Variants 31 to 44 Variant 45 Variants 46 to 59 Variants 60 Variants 61 to 74 Variants 75 and 92 Variants 76 to 86 Variants 87 to 91		60 220 45 205 35 195 30 190 25	°C/W

# **NOTES**

- 1. Table 1(b), Item 1.
- 2. Half the value of Table 1(b), Item 1.
- 3. Pulsed measurement, pulse width = 4.0 µs, p.r.f. = 1.0 kHz.



Rev. 'C'

PAGE 26

ISSUE 1

# TABLE 2 - ELECTRICAL MEASUREMENTS AT ROOM TEMPERATURE - A.C. PARAMETERS

No.	CHARACTERISTICS	SYMBOL	MIL-STD-750	TEST	TEST	LIMITS		UNIT
110.	0174170121401100	OTWIDOL	TEST METHOD	FIG.	CONDITIONS	MIN.	MAX.	ONIT
5	Total Capacitance	Ст	4001	1	V <sub>R</sub> = -6.0V f = 1.0MHz	Not	te 1	pF
6	Minority Carrier Lifetime	<b></b>	-	4	I <sub>F</sub> = 10mA Variants 01 to 15 Variants 16 to 45 Variants 46 to 60 Variants 61 to 75 Variants 76 to 86 Variants 87 to 91 Variant 92	7.0 10 15 35 50 100 80		ns
7	Transition Time	τς	-	4	I <sub>F</sub> = 10mA Variants 01 to 15 Variants 16 to 30 Variants 31 to 45 Variants 46 to 60 Variants 61 to 75 and 92 Variants 76 to 86 Variants 87 to 91		75 150 170 200 250 600 1.5	ps ns

#### **NOTES**

1. See Column 4 of Table 1(a).

# TABLE 3 - ELECTRICAL MEASUREMENTS AT HIGH AND LOW TEMPERATURES

	No. CHARACTERISTICS SY	SYMBOL SPEC. AND/OR TEST METHOD		TEST	LIMITS		UNIT	
L			CONDITIONS	MIN.	MAX.	CIVIT		
	2	Reverse Current 2	I <sub>R2</sub>	As per Table 2	As per Table 2	-	10	μА

#### TABLE 4 - PARAMETER DRIFT VALUES

No.	CHARACTERISTICS	SYMBOL	SPEC.AND/OR TEST METHOD	TEST CONDITIONS	CHANGE LIMITS (Δ)	UNIT
2	Reverse Current 2	I <sub>R2</sub>	As per Table 2	As per Table 2	±10 (1) or (2) ±100 (1)	nA %
3	Forward Voltage	V <sub>F</sub>	As per Table 2	As per Table 2	± 100 (1)	mV .

# **NOTES**


- 1.  $\Delta 1 = \Delta 2$ .
- 2. Whichever is the greater, referred to the initial measurement.



PAGE 27

ISSUE 1

# FIGURE 4 - CIRCUITS FOR ELECTRICAL MEASUREMENTS





Rev. 'C'

PAGE 28

ISSUE 1

# TABLE 5(a) - CONDITIONS FOR HIGH TEMPERATURE REVERSE BIAS BURN-IN

No.	CHARACTERISTICS	SYMBOL	CONDITIONS	UNIT
1	Ambient Temperature	T <sub>amb</sub> + 150(+0-3)		°C
2	Reverse Voltage	V <sub>R</sub>	Note 1	V


#### **NOTES**

1. Half the value of Table 1(b), Item 1.


# TABLE 5(b) - CONDITIONS FOR POWER BURN-IN AND OPERATING LIFE TESTS

No.	CHARACTERISTICS	SYMBOL	CONDITIONS	UNIT
1	Ambient Temperature	T <sub>amb</sub>	+ 125( + 0 - 3)	°C
2	Forward Current	lF	Variants 01 to 30: 100 Variants 31 to 86 and 92: 150 Variants 87 to 91: 250	mA

# FIGURE 5(a) - ELECTRICAL CIRCUIT FOR HIGH TEMPERATURE REVERSE BIAS BURN-IN



# FIGURE 5(b) - ELECTRICAL CIRCUIT FOR POWER BURN-IN AND OPERATING LIFE TESTS





Rev. 'C'

PAGE 29

ISSUE 1

# 4.8 <u>ENVIRONMENTAL AND ENDURANCE TESTS (CHARTS IV AND V OF ESA/SCC GENERIC SPECIFICATION NO. 5010)</u>

#### 4.8.1 <u>Electrical Measurements on Completion of Environmental Tests</u>

The parameters to be measured on completion of environmental tests are scheduled in Table 2. Unless otherwise stated, the measurements shall be performed at  $T_{amb}$  = +22 ±3 °C.

# 4.8.2 <u>Electrical Measurements at Intermediate Points and on Completion of Endurance Tests</u>

The parameters to be measured at intermediate points and on completion of endurance tests are scheduled in Table 6. Unless otherwise stated, the measurements shall be performed at  $T_{amb} = +22 \pm 3$  °C.

# 4.8.3 Conditions for Operating Life Tests (Part of Endurance Testing)

The requirements for operating life testing are specified in Section 9 of ESA/SCC Generic Specification No. 5010. The conditions for operating life testing are specified in Table 5(b) of this specification.

#### 4.8.4 <u>Electrical Circuits for Operating Life Tests</u>

The circuit to be used for performance of the operating life test shall be the same as shown in Figure 5(b) for Power Burn-in.

#### 4.9 TOTAL DOSE IRRADIATION TESTING

# 4.9.1 Application

If specified in Para. 4.2.1 of this specification, total dose irradiation testing shall be performed in accordance with the requirements of ESA/SCC Basic Specification No. 22900.

#### 4.9.2 Bias Conditions

Continuous bias shall be applied during irradiation testing as shown in Figure 6 of this specification.

#### 4.9.3 <u>Electrical Measurements</u>

The parameters to be measured prior to irradiation exposure are scheduled in Table 2 of this specification. Only devices which meet the requirements of Table 2 shall be included in the test sample.

The parameters to be measured during and on completion of irradiation testing are scheduled in Table 7 of this specification.

#### 4.10 SPECIAL TESTING

Not applicable.



Rev. 'A'


PAGE 30

ISSUE 1

# TABLE 6 - ELECTRICAL MEASUREMENTS AT INTERMEDIATE POINTS AND ON COMPLETION OF ENDURANCE TESTING

No. CHARACTERISTICS	SYMBOL	SPEC. AND/OR TEST METHOD	TEST CONDITIONS	LIMITS		1 18 117	
				MIN.	MAX.	UNIT	
1	Reverse Current 1	J <sub>R1</sub>	As per Table 2	As per Table 2	As per Ta	able 2	μΑ
2	Reverse Current 2	I <sub>R2</sub>	As per Table 2	As per Table 2	As per 7	Table 2	nA
3	Forward Voltage	V <sub>F</sub>	As per Table 2	As per Table 2	As per 7	Table 2	V
5	Total Capacitance	C <sub>T</sub>	As per Table 2	As per Table 2	As per 1	Table 2	pF

# FIGURE 6 - BIAS CONDITIONS FOR IRRADIATION TESTING



# **NOTES**

1. A reverse bias of  $V_R$  = Half the value of Table 1(b), Item 1, shall be applied.



Rev. 'A'

PAGE 31


ISSUE 1

# TABLE 7 - ELECTRICAL MEASUREMENTS DURING AND ON COMPLETION OF IRRADIATION TESTING

No.	CHARACTERISTICS	SYMBOL	SPEC. AND/OR TEST METHOD	TEST CONDITIONS	CHANGE LIMITS (Δ)	UNIT
6	Minority Carrier Lifetime	ՇԼ	As per Table 2	As per Table 2	Note 1	%

#### **NOTES**

1. The graph given below shall be used to determine the maximum permitted change.





PAGE 32

ISSUE 1

# APPENDIX 'A'

Page 1 of 1

# AGREED DEVIATIONS FOR M/A-Com LTD. (G.B.)

ITEMS AFFECTED	DESCRIPTION OF DEVIATIONS		
Para. 4.2.2	Para. 9.4, "High Temperature Stabilisation Bake": May be performed at +150(+0-3) °C.		